

November, 2017

3M™ VHB™ Structural Glazing Tape B23F

Product Description

Finite Element Analysis (FEA) data is available for this product at:
3m.com/FEA

3M™ VHB™ Structural Glazing Tapes are fully-cured, durable, high performance double-sided pressure sensitive acrylic foam tapes. They are used for attaching glass and other infill panels to metal frames in curtain wall systems, commercial windows and doors, skylight and canopy systems replacing commonly used mechanical fasteners, gaskets or structural silicone sealants. Application performance history since 1990 and 3rd party test results demonstrate the outstanding durability, UV resistance and temperature performance of 3M™ VHB™ Tape acrylic foam chemistry.



3M™ VHB™ Structural Glazing Tape B23F

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Method	Notes
Color	Black			
Total Tape Thickness	2.3 mm	90 mil	ASTM D3652	
Adhesive	High Performance Acrylic			
Adhesive Carrier	Acrylic Foam (closed cell)			
Density	720 kg/m ³	45 lb/ft ³	ASTM D3574	Foam with adhesive
Liner	Red Polyethylene Film			
Liner Thickness	0.125 mm	5 mil		

Typical Performance Characteristics

Property	Values	Method	Test Name	Substrate	Notes	Temp C	Temp F
----------	--------	--------	-----------	-----------	-------	--------	--------

No data available in table

Showing 0 to 0 of 0 entries

Previous

Next

Table continued on next page

3M™ VHB™ Structural Glazing Tape B23F

Typical Performance Characteristics (continued)

Property	Values		Method	Test Name	Substrate	Notes	Temp C	Temp F
90° Peel Adhesion	52.5 N/cm	30 lb/in	ASTM D3330	90° Peel Adhesion	Anodized Aluminum			
Anodized Aluminum								
Normal Tensile	1480 kPa	70 lb/in ²	ASTM D897	T-Block	Aluminum T-block			
Overlap Shear Strength	450 kPa	65 lb/in ²	ASTM D1002	Overlap Shear Strength	Anodized Aluminum			
Anodized Aluminum								
Short Term Temperature Resistance	149 °C	300 °F				No change in room temperature dynamic shear properties following 4 hour conditioning at indicated temperature with 100 g/static load. (Represents minutes, hour in a process type temperature exposure).		
Long Term Temperature Tolerance	93 °C	200 °F				Maximum temperature where tape supports at least 250 g load per 0.5 in ² in static shear for 10,000 minutes. (Represents continuous exposure for day or weeks).		

Table continued on next page

3M™ VHB™ Structural Glazing Tape B23F

Typical Performance Characteristics (continued)

Property	Values	Method	Test Name	Substrate	Notes	Temp C	Temp F
Minimum Application Temperature	15 °C 60 °F						
Static Shear 23C	1000 g/3.2cm ² 2.2 lb/0.5 in ²	ASTM D3654			Holds 10,000 min.	23C	73F
Static Shear 66C	500 g/3.2cm ² 1.1 lb/0.5 in ²	ASTM D3654			Holds 10,000 min.	66C	150F
Static Shear 93C	500 g/3.2cm ² 1.1 lb/0.5 in ²	ASTM D3654			Holds 10,000 min.	93C	200F

Available Sizes

Property	Values	Test Name
Standard Roll Length	32.9 m 36 yd	
Standard Width	15, 20, 25, 30 mm 1/2, 5/8, 3/4, 7/8, 1, 1-1/8, 1-1/4 in	
Normal Slitting Tolerance	±0.8 mm ±1/32 in	
Core Size	76.2 mm 3 in	ID

3M™ VHB™ Structural Glazing Tape B23F

Design Guidelines

Note: For tape area calculations the following guidelines can be used. Each application should be reviewed by a 3M Application Engineer.

Dynamic Loads:

For dynamic tensile or shear loads, such as wind loads, a design strength of 12 lb/in² (85 kPa) is used for 3M™ VHB™ Structural Glazing Tapes. This design strength guideline provides a safety factor of >5 and was established based on material property testing as well as ASTM dynamic load testing for curtain wall applications.

Static Loads:

For static tensile or shear loads, such as dead weight loads with no mechanical support, snow loads and other long-term loads, a design strength of 0.25 lb/in² (1.7 kPa) is used for 3M™ VHB™ Structural Glazing Tapes. This means 4 in² of tape per 1 lb load (60 cm² of tape per 1 kg load) should be used to support constant stress loads. This guideline provides a safety factor of >5. Dead load support is required for glass panel bonding in most structural glazing applications. Note: Static load and dynamic load calculations should be performed on unsupported dead load structural glazing applications. The calculation resulting in the wider tape width should be used as the appropriate tape width for the specific application.

Differential Movement:

3M™ VHB™ Structural Glazing Tapes can tolerate shear movement up to 3 times its original thickness (300% shear strain). This means 0.090 in (2.3 mm) thick tapes can tolerate shear strain up to 0.27 in (6.9 mm).

Force/Stress:

In general, when designing with 3M™ VHB™ Structural Glazing Tapes, forces acting on the tape should consist of either shear or tensile type stress loads. This allows the stress or force to be applied over the entire tape area. Applications placing cleavage or peel type stress on the tape should be avoided as this will place the stress on the leading edge of the peel or cleaving.

3M™ VHB™ Structural Glazing Tape B23F

Application Guidelines

Application Review:

Project applications with 3M™ VHB™ Structural Glazing Tapes must be reviewed by a 3M Application Engineer. Project drawings must be submitted to 3M to initiate the project-specific application review.

Adhesion Testing:

Adhesion testing must be conducted on project specific substrates to determine the appropriate surface preparation methods leading to high bond strength of the 3M™ VHB™ Structural Glazing Tape. Adhesion testing should be coordinated through a 3M Application Engineer. Adhesion test results will provide guidance on proper surface preparation methods, including cleaning and priming techniques, for project-specific substrates and finishes.

Fabrication Guidelines:

A shop work environment is appropriate for bonding applications with 3M™ VHB™ Structural Glazing Tape. Tape application temperature should be at least 60°F (15°C). Field bonding is only considered for deglaze/reglaze activities but only after consultation with a 3M Application Engineer. It is also important to provide adequate pressure to the tape after it has been applied to the first prepared substrate surface and after the two parts are joined together. A pressure of 15 lb/in² (100 kPa) or greater should be applied over the whole tape area to facilitate good contact of the adhesive to both substrates. Rigid surfaces may require 2 or 3 times more pressure to achieve >15 lb/in² (100 kPa) at the tape bond line. Pressure application methods must achieve acceptable wet-out (contact) of the adhesive to the bonding substrates. 3M Application Engineers or their channel partners are available to provide training of operators for 3M™ VHB™ Structural Glazing Tape bonding applications.

Storage and Shelf Life

The optimum storage conditions are 72°F (22°C) and 50% relative humidity.

3M™ VHB™ Structural Glazing Tapes have a shelf life of 24 months from date of manufacture when stored at 40°F to 100°F (4°C to 38°C) and 0-95% relative humidity.

Trademarks

3M and VHB are trademarks of 3M.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~/~3M-VHB-Structural-Glazing-Tape-B23F?N=5002385+3291242888&rt=rud

Table continued on next page

3M™ VHB™ Structural Glazing Tape B23F

References (continued)

Property	Values
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=B23F

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ VHB™ Structural Glazing Tape B23F

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: 3M warrants for 24 months from the date of 3M manufacture that 3M™ VHB™ Tape will be free of defects in material and manufacture. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. This warranty does not cover damage resulting from the use or inability to use 3M™ VHB™ Tape due to misuse, workmanship in application, or application or storage not in accordance with 3M recommended procedures (except to the extent 3M approves and issues a specific application warranty, for which the customer must apply, receive 3M approval, and meet all applicable warranty and process requirements, the additional details, terms, and conditions of which are available from 3M). If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

3M™ VHB™ Structural Glazing Tape B23F



3M United States
3M Center
St. Paul, MN 55144-1000
800-362-3550
www.3M.com

Please recycle.
© 3M 2021. All Rights Reserved.

The brands listed above are trademarks of 3M

